

**Film Faced Plywood Buildplex**

Essential Characteristics	Performance	Harmonized technical specification
Density	600 – 620 kg/m <sup>3</sup>	-
Humidity	8 – 12%	-
Bending strength (MOR)	35.88 MPa (N/mm <sup>2</sup> )	EN 310
Short duration average modulus of elasticity parallel to grain (MOE)	6090.92 MPa (N/mm <sup>2</sup> )	EN 310
Bonding strength / Shearing test	0.83 (N/mm <sup>2</sup> )	EN 314 – 1&2
Swelling	7.68% (g/cm <sup>3</sup> )	-
Release of formaldehyde (melamine plywood)	Class E2	-
Expected times of re-use	4 – 6 times	-

Technical features according to the manufacturer. All materials commercialised by GLOBALDIS must be installed by a competent technician who complies with the installation standards of the respective product. The guarantee for GLOBALDIS products is subject to compliance with the installation standards indicated.

GLOBALDIS endeavours to constantly improve its offer and therefore reserves the right to make changes to the product range or technical specifications without prior notice.